

# Report® Multiuso Premium



## PREMIUM

### Descrição

Papel reprodutivo alcalino.  
High quality alkaline woodfree paper.

### Principais Usos

Para ser usado em copiadoras e impressoras laser e jato de tinta.  
For copiers, laser and jet printers.

Gramatura / Grammage	Norma Ref. Standard	Unidade Unit	75		80		90	
			N	T	N	T	N	T
Gramatura / Grammage	ISO 536	g/m <sup>2</sup>	75,0	± 3,0	80,0	± 3,2	90,0	± 5,7
Espessura / Thickness	ISO 534	micra	97,0	± 5,0	102,0	± 5,0	117,0	± 6,0
Opacidade / Opacity	ISO 2471	%	90,0	± 88	92,0	± 90	94,0	± 92
Branco CIE / CIE Whiteness	ISO 11475	nº	160	± 3	160	± 3	160	± 3
Alvura ISO / ISO Brightness	ISO 2470	%	100	± 97	100	± 97	100	± 97
Aspereza Bendtsen / Bendtsen Roughness	ISO 8791/2	ml/min	145	± 85	145	± 85,0	170	± 110

N = Nominal

T = Tolerância / Tolerance

Norma Ref = Norma de referência

Standard = Reference method

- Unidade de fabricação / Mill: SUZANO
- Condições de ensaios: 23°C / 50% UR (de acordo com a ISO 187). Tolerâncias: baseadas em 95% do intervalo de confiança, aplicadas para média da resma. Para verificação, a média deve ser calculada em 5 medições de amostras escolhidas aleatoriamente na resma. Deverá estar dentro do limite especificado no menos 19 das 20 resmas analisadas. / Test climate conditions: 23°C / 50% RH (according to ISO 187). Tolerances: based upon 95% confidence limits, apply to room average. In order to verify, room average shall be based on 5 single measurements randomly sampled within the ream. These averages will be for at least 19 of 20 reams within the specification limits.
- Reservamo-nos o direito a alterações. / We reserve the right of changing.
- Para aplicações diferentes das citadas acima, entrar em contato com a Suzano. / For applications other than those mentioned above, contact Suzano.

